

**HEAT-RESISTANT SHEET**

**Patent number:** JP11229290  
**Publication date:** 1999-08-24  
**Inventor:** NISHIOMOTE KENJI; KAJITA SAKAE  
**Applicant:** KURARAY CO LTD  
**Classification:**  
**- International:** D21H13/24; D01F6/84  
**- european:**  
**Application number:** JP19980035563 19980218  
**Priority number(s):**

**Also published as:**



JP11229290 (A)

**Abstract of JP11229290**

**PROBLEM TO BE SOLVED:** To obtain a heat-resistant sheet excellent in specific water absorptivity and shape stability, mechanical performances, or the like, at high temperatures.

**SOLUTION:** This sheet comprises 95-75 wt.% of melt anisotropic polyester fibers (component A) and 5-25 wt.% of heat-resistant fibers (component B) manifesting a negative coefficient of linear expansion at 25-150 deg.C and having  $\geq 300$  deg.C decomposition temperature and  $\geq 550$  g/d tensile modulus of elasticity at 150 deg.C, e.g. p aramid fibers.

---

Data supplied from the **esp@cenet** database - Worldwide